

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
18 March 2004 (18.03.2004)

PCT

(10) International Publication Number
WO 2004/022667 A1

(51) International Patent Classification⁷: **C09K 7/02**,
7/00, E21B 43/25, C08F 220/34, 220/60, 220/56, 226/10,
C08L 33/14, 33/24

73533 (US). **WILSON, Michael, J.** [US/US]; 4413 Odom
Drive, Duncan, OK 73533 (US).

(21) International Application Number:
PCT/GB2003/002953

(74) Agents: **WAIN, Christopher, Paul** et al.; A A Thornton
& Co, 235 High Holbon, London WC1V 7LE (GB).

(22) International Filing Date: 8 July 2003 (08.07.2003)

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VC, VN, YU, ZA, ZM, ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/236,722 6 September 2002 (06.09.2002) US

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **HAL-
LIBURTON ENERGY SERVICES, INC.** [US/US]; P.O.
Box 1431, Duncan, OK 73533 (US).

(71) Applicant (*for MW only*): **WAIN, Christopher, Paul**
[GB/GB]; A.A. Thornton & Co, 235 High Holborn,
London WC1V 7LE (GB).

Published:

— with international search report

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **EOFF, Larry, S.**
[US/US]; 2201 Cedar, Duncan, OK 73533 (US). **REDDY,
Raghava, B.** [IN/US]; 2013 Waverly Drive, Duncan, OK

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: COMPOSITIONS FOR AND METHODS OF STABILIZING SUBTERRANEAN FORMATIONS CONTAINING
CLAYS

(57) Abstract: A composition of matter for use in stabilizing shale formations in earth boreholes comprising polymeric products,
e.g., polymers of a dialkyl aminoalkyl methacrylate, which can optionally be quaternized with an alkyl halide to produce drilling
fluid additives which stabilize borehole formations containing reactive clays in the presence of an aqueous medium.

WO 2004/022667 A1

COMPOSITIONS FOR AND METHODS OF STABILIZING SUBTERRANEAN FORMATIONS CONTAINING CLAYS

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION

The present invention relates to polymeric compositions that can be used to stabilize reactive clays in subterranean formations and to a method of
5 stabilizing such reactive clays.

DESCRIPTION OF THE PRIOR ART

In the drilling of oil and gas wells and other such boreholes, it is generally necessary to use a drilling fluid that performs a variety of functions but is
10 primarily used to lubricate the drill bit and carry the cuttings to the surface. It is not uncommon to encounter formations during the drilling process that are argillaceous. These argillaceous formations contain clay (shale) particles, the proportion of which can vary over a wide range. When these argillaceous formations are encountered, and if a water based drilling fluid is employed,
15 complex chemical reactions take place within the argillaceous formation, including ion exchange, hydration, etc. These reactions result in swelling, crumbling or dispersion of the clay or shale particles in the formation through which the drill bit passes. Indeed, the problems can become so severe that washout and even complete collapse of the borehole can occur.

In an attempt to solve these problems, additives are included in the aqueous drilling fluid that are designed to arrest or slow down fluid invasion into the formation by forming an impermeable or semi-impermeable membrane on the surface of the borehole. For example, sodium silicate-based drilling fluids

5 are believed to form such semi-impermeable membranes and are commonly used for maintaining shale stability. Other drilling fluid systems have also been used to deal with the problem of shale stabilization. For example, U.S. Patent No. 4,299,710 discloses a drilling fluid comprising an aqueous solution of a combination of thickeners such as a copolymer and a polysaccharide.


10 Additionally, U.S. Patent No. 5,972,848 discloses a method for stabilizing shale formations by employing an aqueous solution containing a polymer with a hydrophilic group and a hydrophobic group.

SUMMARY OF THE INVENTION

15 In one preferred aspect, the present invention provides a composition of matter comprising a polymeric product selected from the group consisting of:

(1) polymers of a first monomeric component selected from the group consisting of (a) compounds having the formula:

20



wherein Z is oxygen or NH, R₁ is H or CH₃, R₂ and R₃ are independently alkyl groups containing from 1 to 3 carbon atoms, and n is from 1 to 3, (b) quaternized compounds of Formula I obtained by reacting compounds of Formula I with an alkyl halide having the formula:



wherein R₄ is an alkyl group containing from 1 to 22 carbon atoms and X is a halide ion, and (c) mixtures of (a) and (b),

10 (2) polymers of compounds having the Formula I which have been polymerized and then quaternized with compounds having the Formula II,

(3) polymeric mixtures of (1) and (2), and

(4) polymers of compound (a) or (b) and a second monomeric component selected from the group consisting of (d) vinyl pyrrolidone (e)

15 compounds of the formula:



and mixtures of (d) and (e),

(5) polymers of compounds (d) and (e) provided that Z is NH,

20 (6) polymeric mixtures of (1) and (4), and

(7) polymeric mixtures of (2) and (4).

In another preferred aspect of the present invention, there is provided a method of stabilizing borehole formations containing reactive clays in the presence of water comprising contacting the formation with an aqueous medium


containing of a polymeric product as described above.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

In a preferred form, the present invention involves hydrophobically
 5 modifying water-soluble polymers by adding water-insoluble groupings into the
 polymer to an extent that does not render the water-soluble polymer insoluble
 in water; i.e., its water solubility remains.

As can be seen from the formulas above, the composition of the present
 invention can take the form of a number of polymeric products which include:

10



15

wherein Z is oxygen or NH, R₁ is H or CH₃, R₂ and R₃ are independently alkyl
 groups containing from 1 to 3 carbon atoms, and n is from 1 to 3, (b) quaternized
 compounds of Formula I obtained by reacting compounds of Formula I with an
 alkyl halide having the formula:

20



wherein R₄ is an alkyl group containing from 1 to 22 carbon atoms and X is a
 halide ion, and (c) mixtures of (a) and (b),

- (2) polymers of compounds having the Formula I which have been
 polymersized and then quaternized with compounds having the Formula II,
 (3) polymeric mixtures of (1) and (2), and
 (4) polymers of compound (a) or (b) and a second monomeric
 5 component selected from the group consisting of (d) vinyl pyrrolidone (e)
 compounds of the formula:



- and mixtures of (d) and (e),
 10 (5) polymers of compounds (d) and (e) provided that Z is NH,
 (6) polymeric mixtures of (1) and (4), and
 (7) polymeric mixtures of (2) and (4).

Compounds having the Formulas I and III can comprise an
 acrylic/methacrylic acid derivative, referred to herein generally as "acrylic acid
 15 derivative".

Generally speaking, when the first and second monomeric components
 are used to form a copolymer, the molar ratio of the first monomeric component
 to the second monomeric component will be from about 2:98 to 10:90.

The polymers of the present invention can be prepared by several
 20 methods. For example, if one desires to use a polymer of compounds having
 Formula I, a homopolymer can be made. Where first and second monomeric
 components are employed, one of the first monomeric components can be

reacted with one of the second monomeric components to produce a co-polymer of the first and second monomeric components. It will also be apparent that many other variations of preparing the compositions of the present invention can be employed. Thus, a co-polymer can be made from an acrylic acid derivative
5 having the structure of the Formula I and a quaternized version of the acrylic acid derivative having the structure of Formula I.

As can also be seen, polymer products obtained by mixing polymers described above can be employed. In yet another method, the acrylic acid derivative that has not been quaternized can be polymerized to form a polymer
10 of the desired molecular weight, following which it can be quaternized to the desired degree by reaction with the alkyl halide.

The molecular weight of the polymers of the present invention can vary over wide limits with molecular weights (wt. average) ranging from 50,000 to 500,000 being considered "low" molecular weight polymers, while copolymers
15 having molecular weights ranging from 500,000 to 5,000,000 being considered "high" molecular weight polymers.

The modified, i.e., quaternized polymers, of the present invention can be made by two methods:

Method 1

20 In this method, the acrylic acid derivative is reacted with the desired alkyl halide, which results in the alkyl halide attaching to the terminal nitrogen and quaternization of the nitrogen. This modified, quaternized monomer is isolated

and can then be copolymerized with more of the acrylic acid derivative, (Formula I), vinyl pyrrolidone, a compound of Formula III or a mixture thereof.

Method 2

5 In this method, the acrylic acid derivative, as described in Formula I, is homopolymerized, following which this polymer is reacted with a suitable alkyl halide in the presence of a surfactant. The surfactant is necessary because of the fact that the alkyl halide is not water soluble whereas the polymerized acrylic acid derivative is. Accordingly, the surfactant acts to solubilize the alkyl halide
10 such that it can react with the terminal nitrogen of the acrylic acid derivative.

 The polymers of the present invention have been shown in laboratory testing to vastly reduce shale erosion. A shale erosion test is commonly employed to determine the ability of a drilling fluid and/or the additives therein to prevent a shale from eroding in the presence of an aqueous medium such as
15 an aqueous based drilling fluid. Such erosion, when encountered in actual field conditions in a borehole, and as noted above, can lead to problems ranging from a washout to a complete collapse of the borehole.

 A typical shale erosion test is conducted by rolling a weighed portion of sized shale particles in an aqueous medium and then screening the particles to
20 determine the amount of shale that eroded to the point of passing through a selected sized screen. In the shale erosion test used with the compositions of the present invention, U.S. Standard Sieve Series No. 6 and No. 14 screens

were employed. The shale was crushed and ground into particles that passed through the 6 mesh screen but were retained on the 14 mesh screen; i.e., particles of a size (-6+14) were used for the erosion test. Equal portions (40.00 g) of the shale were put into one laboratory barrel (350 ml) of each of the various
5 test drilling fluids and rolled at 150°F for 16 hours. The drilling fluids were then screened through the 14 mesh screen and the retained solids were washed, dried, and weighed. The percent of erosion was calculated based on the weight loss, corrected for the moisture content (7.67%) of the original sample.

The composition of the present invention can be used in fluid for treating
10 subterranean formations including, but not limited to, drilling fluids, completion fluids, remedial fluids and the like. In the method according to the present invention, a drilling fluid containing one of the compositions described above would be incorporated in a suitable amount, e.g., from 1 to 20 lbs/bbl, in the drilling mud or fluid, which, in the conventional fashion, would be circulated in the
15 borehole during the drilling operation. If, during the drilling operation, a formation were encountered that contained a reactive clay, e.g., a clay that had a tendency to erode in the presence of water, the presence of the polymer compositions of the present invention would stabilize the shale, minimizing or ideally stopping the erosion. It is also to be understood that in addition to
20 incorporating the compositions of the present invention in drilling fluids or muds, it can be also used in other downhole fluids under certain circumstances when it is desired to stabilize shale formations.

To more fully illustrate the present invention, the following non-limiting examples are presented:

Example 1

A series of polymers was prepared according to Method 1 described
5 above. To prepare a quaternized monomer of Formula I, to a 100 mL round
bottom flask is added 16.7 grams of dimethylaminoethyl methacrylate (DMEMA)
and 16.2 grams of hexadecyl bromide. The mixture is heated to 110° F and
stirred for 24 hours. The mixture is then poured into 1 liter of petroleum ether,
resulting in precipitation of the quaternized monomer. The monomer is collected
10 on a Buchner funnel, washed with excess petroleum ether, collected, and dried
in a vacuum dessicator.

To prepare a copolymer, to a 250 ml round bottom flask charge the
following: 3.8 grams of DMEMA, 0.7 grams of the quaternized monomer
described above, 84.5 grams water, and 1.2 grams concentrated sulfuric acid
15 (to achieve a pH of ~7.1). This solution is then sparged with nitrogen for 30
minutes, followed by the addition of 0.035 grams 2,2'-azobis (2-amidinopropane)
dihydrochloride. The resulting solution is then heated under a nitrogen
atmosphere, with stirring, to 110°F and held for 18 hours to produce a highly
viscous polymer solution. In all of the test samples in this example, the acrylic
20 acid derivative employed was DMEMA. The alkyl halide employed was an alkyl
bromide, the carbon number appearing in the column labeled "Monomeric
Component 1" referring to the chain length of the alkyl group. Except as

otherwise indicated, each sample contained 1% by weight of the polymer in deionized water. The results are shown in Table 1 below.

Table 1

5	Sample	Monomeric ³ Component 1 (Mole %)	Monomeric Component 2	Relative Molecular Weight	% Erosion
	1	-	DMEMA	High	17
	2 ¹	6% C ₁₀	"	"	7
	3	"	"	"	0
	4	10% C ₁₆	"	"	1
10	5	15% C ₁₆	"	"	-1
	6	20% C ₁₆	"	"	-1
	7	30% C ₁₆	"	"	11
	8 ²	4% C ₁₈	"	"	7
	9	-	"	Low	10
15	10	6% C ₁₆	"	"	17
	11	15% C ₁₆	"	"	18

¹2.3 wt. % polymer in water.

²1.6 wt. % polymer in water.

20 ³Molar percent of quaternized DMEMA in copolymer.

Example 2

In this example, the polymers were also prepared according to the procedure of Method 1 as described above with respect to Example 1. In all cases, the acrylic acid derivative employed was DMEMA, and, unless indicated otherwise, each sample contained 1% by weight of the polymer in deionized water. The results are shown in Table 2 below.

Table 2

Sample	Monomeric ² Component 1 (Mole %)	Monomeric Component 2	Relative Molecular Weight	% Erosion
1	-	VP	High	33
2	6% C ₁₆	"	"	2
3	"	"	Low	44
4	10% C ₁₆	"	"	16
5	20% C ₁₆	"	-	4.6

¹Vinyl pyrrolidone.

²Molar percent of quaternized DMEMA as per Formula III in copolymer.

Example 3

In this example, a copolymer was prepared according to Method 2 described above. A homopolymer of DMEMA is prepared as follows. To a 3 L round bottom flask is added 1968.0 grams of water, and this is sparged with nitrogen for 1.5 hours. Next is added 105.0 grams of DMEMA, 25.8 grams concentrated sulfuric acid (to achieve a pH of ~7.9) and 0.46 grams 2,2'-azobis (2-amidinopropane) dihydrochloride. The mixture is then heated under a nitrogen atmosphere, with stirring, to 110°F and held for 18 hours to produce a highly viscous polymer solution.

The copolymer is produced as follows. To a 250 mL round bottom flask is added 71.0 grams of the DMEMA homopolymer, as described above, followed by 4.0 grams 15% NaOH (to achieve a pH of ~8.9). Next is added 54.6 grams water, 0.36 grams hexadecyl bromide and 0.39 grams

benzylcetyldimethylammonium bromide. This mixture is then heated, with stirring, to 140°F for 24 hours.


The copolymer produced contained 6% (molar) of hexadecyl bromide and was of high molecular weight. A 1% by weight solution of the polymer in
5 deionized water exhibited 0% erosion.

As can be seen from Table 1, a homopolymer of DMEMA which has not been quaternized exhibits some degree of erosion control. It has also been found that a homopolymer of DMEMA subsequently quaternized with hexadecyl bromide and of high molecular weight exhibits a -2% erosion. The foregoing
10 description and examples illustrate selected embodiments of the present invention. In light thereof, variations and modifications will be suggested to one skilled in the art, all of which are in the spirit and purview of this invention.

CLAIMS

A composition of matter comprising a polymeric product selected from the group consisting of:

5



- 10 wherein Z is oxygen or NH, R₁ is H or CH₃, R₂ and R₃ are independently alkyl groups containing from 1 to 3 carbon atoms, and n is from 1 to 3, (b) quaternized compounds of Formula I obtained by reacting compounds of Formula I with an alkyl halide having the formula:



II

15

wherein R₄ is an alkyl group containing from 1 to 22 carbon atoms and X is a halide ion, and (c) mixtures of (a) and (b),

- (2) polymers of compounds having the Formula I which have
20 been polymersized and then quaternized with compounds having the Formula II,

(3) polymeric mixtures of (1) and (2), and

(4) polymers of compound (a) or (b) and a second monomeric

component selected from the group consisting of (d) vinyl pyrrolidone (e)
compounds of the formula:



5

and mixtures of (d) and (e),

- (5) polymers of compounds (d) and (e) provided that Z is NH,
- (6) polymeric mixtures of (1) and (4), and
- (7) polymeric mixtures of (2) and (4).

10

2. The composition of Claim 1 wherein said first monomeric
component comprises quaternized dimethylaminoethyl methacrylate.

3. The composition of Claim 1 wherein said first monomeric
15 component comprises dimethylaminoethyl methacrylate.

4. The composition of Claim 1 wherein said second monomeric
component comprises vinyl pyrrolidone.

20 5. The composition of Claim 1 wherein said second monomeric
component comprises compounds having the Formula III.

6. The composition of Claim 1 wherein said first monomeric component and said second monomeric component are in a molar ratio of from 2:98 to 10:90, respectively.

5 7. The composition of Claim 1 wherein said alkyl halide comprises an alkyl bromide.

8. A method of stabilizing borehole formations containing reactive clays in the presence of water comprising:

10 contacting said formation with an aqueous medium comprising a composition according to any one of Claims 1-7.

9. A fluid for use in borehole operations comprising an aqueous medium and an effective amount of a composition according to any one of
15 Claims 1-7.

10. A method of treating a subterranean formation comprising:
contacting said formation with a fluid comprising a composition according
to any one of Claims 1-7.

INTERNATIONAL SEARCH REPORT

PCT/GB 03/02953

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09K7/02 C09K7/00 E21B43/25 C08F220/34 C08F220/60
C08F220/56 C08F226/10 C08L33/14 C08L33/24

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09K E21B C08F C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 2 221 940 A (BAROID TECHNOLOGY INC) 21 February 1990 (1990-02-21) abstract; claims	1-3, 5, 6, 9, 10
X	US 4 699 722 A (DYMOND BRIAN ET AL) 13 October 1987 (1987-10-13) the whole document	1, 4-6, 9, 10
X	US 5 342 530 A (AFTEN CARL W ET AL) 30 August 1994 (1994-08-30) column 3; claims 1, 5, 12, 14	1-3, 6, 8-10
X	US 4 563 292 A (BORCHARDT JOHN K) 7 January 1986 (1986-01-07) abstract; claim 6; tables 1, 2	1-3, 9, 10
	-/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

26 September 2003

Date of mailing of the international search report

07/10/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Pollio, M

INTERNATIONAL SEARCH REPORT

PCT/GB 03/02953

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 22 50 552 A (GAF CORP) 18 April 1974 (1974-04-18) the whole document -----	1-7
X	US 4 554 081 A (BORCHARDT JOHN K ET AL) 19 November 1985 (1985-11-19) abstract; claims 1,3,7; table 2 -----	1-3,5,9, 10
X	US 4 959 432 A (FAN YOU-LING ET AL) 25 September 1990 (1990-09-25) column 3; claim 1; tables 1,2 -----	1,5-7
X	US 4 627 926 A (LUNDBERG ROBERT D ET AL) 9 December 1986 (1986-12-09) abstract -----	1,4,6,9, 10
X	US 3 910 862 A (FEIN MARVIN M ET AL) 7 October 1975 (1975-10-07) abstract -----	1-4,6
X	US 3 434 971 A (ATKINS BOBBY L) 25 March 1969 (1969-03-25) the whole document -----	1,4-6,9, 10

INTERNATIONAL SEARCH REPORT

PCT/GB 03/02953

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 2221940	A	21-02-1990	AU 633262 B2	28-01-1993
			AU 3953589 A	15-02-1990
			BR 8904091 A	27-03-1990
			CA 1332502 C	18-10-1994
			DE 3926970 A1	22-02-1990
			DK 398889 A	16-02-1990
			IT 1232916 B	05-03-1992
			NL 8902056 A	01-03-1990
			NO 893150 A	16-02-1990
			SG 128992 G	12-03-1993
US 4699722	A	13-10-1987	CA 1251627 A1	28-03-1989
			GB 2159858 A ,B	11-12-1985
			NO 852136 A ,B,	02-12-1985
US 5342530	A	30-08-1994	US 5099923 A	31-03-1992
			US 5152906 A	06-10-1992
US 4563292	A	07-01-1986	EP 0212019 A1	04-03-1987
			AT 41469 T	15-04-1989
			DE 3568820 D1	20-04-1989
DE 2250552	A	18-04-1974	DE 2250552 A1	18-04-1974
			BE 762235 A1	01-07-1971
			BE 790547 A4	25-04-1973
			CA 937350 A1	20-11-1973
			DE 2103898 A1	12-08-1971
			ES 387802 A1	16-05-1973
			FR 2077143 A5	15-10-1971
			FR 2203831 A2	17-05-1974
			GB 1331819 A	26-09-1973
			GB 1410235 A	15-10-1975
			IL 36092 A	14-03-1974
			IT 1054109 B	10-11-1981
			SE 375780 B	28-04-1975
			US 3910862 A	07-10-1975
			ZA 7100587 A	24-11-1971
US 4554081	A	19-11-1985	NONE	
US 4959432	A	25-09-1990	CA 1302003 C	26-05-1992
US 4627926	A	09-12-1986	NONE	
US 3910862	A	07-10-1975	BE 762235 A1	01-07-1971
			BE 790547 A4	25-04-1973
			CA 937350 A1	20-11-1973
			DE 2103898 A1	12-08-1971
			DE 2250552 A1	18-04-1974
			ES 387802 A1	16-05-1973
			FR 2077143 A5	15-10-1971
			FR 2203831 A2	17-05-1974
			GB 1331819 A	26-09-1973
			GB 1410235 A	15-10-1975
			IL 36092 A	14-03-1974
			IT 1054109 B	10-11-1981
			SE 375780 B	28-04-1975
			ZA 7100587 A	24-11-1971

PCT/GB 03/02953

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3434971	A	25-03-1969	NONE